



# TECHNICAL BULLETIN

Raybo Chemical Company

TELEPHONE: 304-525-5171

## RAYBO 74 — ReleaseAir

REFERENCE	FEATURES	SYSTEM	COMMENTS	USAGE (%)	REFERENCE
	Eliminates Air Entrainment	Solvent	Use for Primer and Topcoat	0.5-1.5% of Total Weight	

### PERFORMANCE

RAYBO 74 was developed to control air entrainment commonly encountered during spray application of high solids coatings. The use of RAYBO 74 is very effective in eliminating this problem. It is also useful for eliminating pinholing and cratering caused by solvent popping in lower solids solvent borne systems.

RAYBO 74 is compatible with most resin systems. It is a resinous polymer which becomes an integral part of the film and does not migrate to the surface causing intercoat adhesion problems. RAYBO 74 is a solution in methyl amyl ketone. It is also soluble in esters, aromatics, glycol ethers, alcohols and other solvents, however, its solubility in 100% aliphatics is limited, although often sufficient to allow the use of RAYBO 74.

### ADVANTAGES

- Compatible with most resin systems
- Does not migrate to surface
- Solids listed with USDA

### RECOMMENDATIONS

For Eliminating Air Entrainment - 0.5-1.5% of Total Weight  
May be added at any stage. May be more effective with grind addition.  
Not recommended for moisture cure urethanes.

### PHYSICAL DATA\*\*

Solids Content . . . . . 50% by wt.  
 Weight/Gallon . . . . . 8.3 lbs.  
 Viscosity . . . . . 15 sec. #2 Zahn cup  
 Flash Point, TCC . . . . . 105°F  
 Appearance . . . . . Water White Liquid

### CONTAINER SIZES

North American: 5 gal. pail\*, 55 gal. drum, and bulk.  
Global Zones: 5 gal. pail\*, 55 gal. drum.

\* One gallon containers available upon request.

\*\* Typical Properties; not sales specifications.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty either expressed or implied, is made or intended. Use by customer should be based upon its own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

 Performance Additives  
 Department  
 Huntington, WV 25721  
 Tel.: 304-525-5171  
 Fax: 304-525-2921

U.S. Marketing Division  
 Raybo Chemical Company  
 Huntington, WV 25721  
 Tel.: 304-525-5172  
 Fax: 304-525-2921

 Exclusive Export  
 Management Company  
 W. R. Mangus, Inc.  
 Tel.: 312-263-6124  
 Email: rwmagnus@cocexport.com



Global Dist. Zones:  
 Representatives in  
 31 Countries